

an organic solvent, wherein said positive active material composition is prepared by physically mixing said positive active material, said binder in said organic solvent in a form of slurry.

Please add the following new claims:

--8. (New) The positive active material composition of claim 1, wherein said organic solvent is N-methylpyrrolidone.

9. (New) The method of claim 5, wherein said organic solvent is N-methylpyrrolidone.

10. (New) The positive active material composition of claim 1 wherein the lithiated transition metal compound is a compound represented by formula:




where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

11. (New) The positive active material composition of claim 1 wherein the lithiated transition metal compound is a compound represented by formula:



where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

12. (New) The positive active material composition of claim 1 wherein the lithiated transition metal compound is a compound represented by formula:




where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

13. (New) The positive active material composition of claim 1 wherein the lithiated transition metal compound is a compound represented by formula:




where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

14. (New) The positive active material composition of claim 1 wherein the lithiated transition metal compound is a compound represented by formula:



where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

15. (New) The positive active material composition of claim 1 wherein the lithiated transition metal compound is a compound represented by formula:



Sub
C1
Cult

where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

16. (New) The positive active material composition of claim 1 wherein the lithiated transition metal compound is a compound represented by formula:




where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

17. (New) The positive active material composition of claim 1 wherein the lithiated transition metal compound is a compound represented by formula:



where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

18. (New) The positive active material composition of claim 1 wherein the lithiated transition metal compound is a compound represented by formula:




where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group

Sub
C1
centd
Handwritten signature

consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

19. (New) The positive active material composition of claim 1 wherein the lithiated transition metal compound is a compound represented by formula:



where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

20. (New) The positive active material composition of claim 1 wherein the lithiated transition metal compound is a compound represented by formula:




where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

21. (New) The positive active material composition of claim 1 wherein the lithiated transition metal compound is a compound represented by formula:



where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

22. (New) The positive active material composition of claim 1 wherein the lithiated transition metal compound is a compound represented by formula:



where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

23. (New) The method of claim 5 wherein the lithiated transition metal compound is a compound represented by formula:




where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

24. (New) The method of claim 5 wherein the lithiated transition metal compound is a compound represented by formula:



where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

25. (New) The method of claim 5 wherein the lithiated transition metal compound is a compound represented by formula:



Sub
Cental


where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

26. (New) The method of claim 5 wherein the lithiated transition metal compound is a compound represented by formula:




where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

27. (New) The method of claim 5 wherein the lithiated transition metal compound is a compound represented by formula:



where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

28. (New) The method of claim 5 wherein the lithiated transition metal compound is a compound represented by formula:



where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group

consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

29. (New) The method of claim 5 wherein the lithiated transition metal compound is a compound represented by formula:



where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

30. (New) The method of claim 5 wherein the lithiated transition metal compound is a compound represented by formula:




where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

31. (New) The method of claim 5 wherein the lithiated transition metal compound is a compound represented by formula:



where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

32. (New) The method of claim 5 wherein the lithiated transition metal compound is a compound represented by formula:



where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

33. (New) The method of claim 5 wherein the lithiated transition metal compound is a compound represented by formula:




where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

34. (New) The method of claim 5 wherein the lithiated transition metal compound is a compound represented by formula:



where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

35. (New) The method of claim 5 wherein the lithiated transition metal compound is a compound represented by formula:



Sub
20
where $1.0 \leq x \leq 1.1$, $0.01 \leq y \leq 0.1$, $0.01 \leq z \leq 0.5$, M' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Co, Mg, La, Ce, Sr and V, M'' is at least one transition metal or lanthanide metal selected from the group consisting of Al, Cr, Mn, Fe, Mg, La, Ce, Sr and V, A is selected from O, F, S or P, and B is Ni or Co.

36. (New) The method of claim 5 wherein the semi-metal is at least one semi-metal selected from the group consisting of Si, B, Ti, Ga, Ge and Al, and the metal is at least one metal selected from the group consisting of Ca, Mg, Sr and Ba.--
